

Data sheet

# Superwool® Boards

MANUFACTURED IN EUROPE

Metric information - Page 2 - 3

## Description

**Rigid boards manufactured** using Superwool® Plus™ and Superwool HT™ fibres, refractory fillers, organic and inorganic binders.

## Type

Rigid boards from high temperature, low biopersistent insulation wools.

## Classification temperature

From 900°C to 1300°C.

The maximum continuous use temperature depends on the application. Unaffected by most chemicals except strong alkalis, phosphoric acid and molybdenum. For further advise please contact your local Morgan Advanced Materials representative.

## Grades available

### Superwool® Plus™ Boards

#### Board 75:

suitable for all applications up to 900°C.

#### H board:

recommended when a high strength material is required.

#### Board 85:

suitable for all applications up to 1000°C.

#### Board LTI:

recommended for all applications where thin, rigid insulating panels are required.

#### Board INO:

recommended for all applications where minimal smoke or fume emission is desirable.

#### Board Aluboard:

a thin aluminium foil is glued on the surface.

### Superwool® HT™ Board

#### Superwool® HT™ Board:

offers the highest classification temperature.

#### Superwool® HT™ C Board:

formula specially designed for application up to 1000°C requiring cycling resistance and high mechanical performances.

#### Superwool® HT WB Board:

was especially developed for the higher operating temperature ranges of the Domestic Wall Hung Boiler Market.

#### Superwool® HT™ SB board:

was especially developed for the Domestic Floor-Mounted (Stand) Boiler Market.

## Benefits

- Thin boards is easily die-cut and all boards can be cut with a hacksaw blade allowing precise shapes to be made.
- Good thermal shock resistance allows use in applications where large variations in temperature occur.
- Low heat storage capacity.
- Can be used in direct contact with flame.
- Very low thermal conductivity.
- Superwool® fibre meets the requirements specified under NOTE Q of European Regulation 1272/2008. All Superwool® fibre products are therefore exonerated from labelling requirements in Europe. No requirement for warning labels under Globally Harmonised System (GHS) for the classification and labelling of chemicals.



Data sheet

MANUFACTURED IN EUROPE

# Superwool® Plus Board

	Superwool Plus Board 75	Superwool Plus Board H	Superwool Plus Board 85	Superwool Plus Board LTI	Superwool Plus Board INO	Superwool Plus Aluboard
<b>Classification temperature</b> °C	900	900	1000	1100	1100	600
<b>Thickness range</b> mm	25 - 50	10 - 25	20 - 50	6 - 15	10 - 20	25
<b>Colour</b>	White/Tan	White/Tan	White/Tan	White/Tan	White/Tan	White/Tan
<b>Density, kg/m<sup>3</sup></b>	320	520	320	350	500	320
<b>Modules of rupture, MPa</b> *unfired	0.8	3.5	0.8	1.5	1.2	1.0
<b>Compressive strength, MPa</b> (ASTM C-165) @ 10% relative deformation	0.4	1.1	0.3	0.3	0.3	0.3
<b>Water absorption after 2 hours</b> %	2.0	2.0	2.0	-	-	-
<b>Loss of ignition after 2 hours</b> @800°C	5.0	10.0	5.0	5.0	5.0	5.5
<b>Permanent linear shrinkage</b> (ASTM C-165) Isothermal heating at class temperature	1.0	1.2	0.9	1.0	1.6	1.4
<b>Thermal conductivity</b> (ASTM C-201) W/m•K						
Mean temperature @ 300°C	0.09	0.12	0.07	0.08	0.09	0.08
@ 400°C	0.07	0.13	0.08	0.09	0.11	0.09
@ 500°C	0.09	-	0.08	-	-	0.10
@ 600°C	0.12	0.15	0.11	0.12	0.13	-
@ 800°C	0.13	-	0.12	0.15	0.15	-
@ 1000°C	-	-	0.16	-	-	-
<b>Chemical composition</b> (ISO 12677) %						
SiO <sub>2</sub>	59.4	70.5	59.5	67.0	63.5	61.2
Al <sub>2</sub> O <sub>3</sub>	15.1	11.2	10.1	4.4	10.6	13.9
Fe <sub>2</sub> O <sub>3</sub> +TiO <sub>2</sub>	3.8	1.6	1.2	0.6	1.5	3.0
CaO+MgO	19.4	15.1	28.2	27.4	23.5	18.3
Na <sub>2</sub> O+K <sub>2</sub> O	2.3	1.6	1.0	0.6	0.9	3.6

**Tolerances**

<b>Superwool Plus Board H</b>	<b>10 - 20 :</b> Maxi +/-1	<b>25 :</b> Maxi +/-2
<b>Superwool Plus Board 85</b>	<b>20 :</b> Maxi +/-1	<b>25 - 50 :</b> Maxi +/-2
<b>Superwool Plus Board LTI</b>	<b>6 - 9 :</b> Maxi +/-0.5	<b>10 - 15 :</b> Maxi +/-1
<b>Superwool Plus Board INO</b>	<b>10 - 20 :</b> Maxi +/-1	
<b>Superwool Plus Board Aluboard</b>	<b>25 :</b> Maxi +/-2	

**Availability and Packaging**

Standard Sizes 1200mm x 1000mm other dimensions available on request.

**Superwool® Plus Aluboard** available in size 1600mm x 900mm.

All Boards can be packed in cartons or on pallets which are shrink wrapped with recyclable plastic.

**Contact**

**Europe:**

Telephone:  
+44 (0) 151 334 4030

E-mail:  
marketing.tc@morganplc.com

**North America:**

Telephone:  
+1 (706) 796 4200

E-mail:  
northamerica.tc@morganplc.com

**South America:**

Telephone:  
+54 (11) 4373 4439

E-mail:  
marketing.tc@morganplc.com

**Asia:**

Telephone:  
+65 6595 0000

E-mail:  
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

**SUPERWOOL®** is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request). **SUPERWOOL®** products may be covered by one or more of the following patents, or their foreign equivalents:

**SUPERWOOL® PLUS** and **SUPERWOOL® HT** products are covered by patent numbers: US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773

## Data sheet

MANUFACTURED IN EUROPE

# Superwool® HT Board

		Superwool HT Board	Superwool HT C Board	Superwool HT WB Board	Superwool HT SB Board
Classification temperature	°C	1300	1150	1150	1150
Thickness range	mm	10 - 50	6-15 / 20-50	6 - 18	20 - 50
Colour		White/Tan	White/Tan	White/Tan	White/Tan
Density, kg/m <sup>3</sup>		360	480 / 380	480	380
Modules of rupture, MPa	*unfired	1.4	1.2	2.6	1.4
Compressive strength, MPa (ASTM C-165) @ 10% relative deformation		0.3	0.3	0.6	0.5
Loss of ignition after 2 hours	@800°C	3.0	5.5	5.5	5.5
Permanent linear shrinkage (ASTM C-165) Isothermal heating at class temperature		1.5	1.3	1.3	1.6
Thermal conductivity (ASTM C-201) W/m•K					
Mean temperature	@ 200°C	0.05	0.06	-	-
	@ 300°C	-	-	0.07	0.07
	@ 400°C	0.08	0.09	0.09	0.09
	@ 600°C	0.11	0.12	0.12	0.12
	@ 800°C	0.15	0.15	0.15	0.15
	@ 1000°C	0.20	-	-	-
	@ 1200°C	0.26	-	-	-
Chemical composition (ISO 12677)	%				
	SiO <sub>2</sub>	77.5	73.0	73.0	71.9
	Al <sub>2</sub> O <sub>3</sub>	1.4	7.9	7.9	6.1
	Fe <sub>2</sub> O <sub>3</sub> +TiO <sub>2</sub>	0.1	1.1	1.1	0.9
	CaO+MgO	20.3	16.8	16.8	20.0
	Na <sub>2</sub> O+K <sub>2</sub> O	0.7	1.2	1.2	1.1

## Tolerances

Superwool Plus HT Board	10 - 20 : Maxi +/-1	25 - 50 : Maxi +/-2		
Superwool Plus HT C Board	6 : Maxi +/-0.5	10 - 20 : Maxi +/-1	25 - 50 : Maxi +/-2	
Superwool Plus HT WB Board	6 - 8 : Maxi +/-0.5	9 - 18 : Maxi +/-1		
Superwool Plus HT SB Board	6 : Maxi +/-0.5	10 - 20 : Maxi +/-1	25 - 50 : Maxi +/-2	

## Availability and Packaging

Standard Sizes 1200mm x 1000mm other dimensions available on request.

## Contact

## Europe:

 Telephone:  
+44 (0) 151 334 4030

 E-mail:  
marketing.tc@morganplc.com

## North America:

 Telephone:  
+1 (706) 796 4200

 E-mail:  
northamerica.tc@morganplc.com

## South America:

 Telephone:  
+54 (11) 4373 4439

 E-mail:  
marketing.tc@morganplc.com

## Asia:

 Telephone:  
+65 6595 0000

 E-mail:  
asia.mc@morganplc.com

Whilst the values and application information in this datasheet are typical, they are given for guidance only. The values and the information given are subject to normal manufacturing variation and may be subject to change without notice. Morgan Advanced Materials – Thermal Ceramics makes no guarantees and gives no warranties about the suitability of a product and you should seek advice to confirm the product's suitability for use with Morgan Advanced Materials - Thermal Ceramics.

**SUPERWOOL®** is a patented technology for high temperature insulation wools which have been developed to have a low bio persistence (information upon request). **SUPERWOOL®** products may be covered by one or more of the following patents, or their foreign equivalents:

**SUPERWOOL® PLUS** and **SUPERWOOL® HT** products are covered by patent numbers: US5714421 and US7470641, US7651965, US7875566, EP1544177 and EP1725503 respectively.

A list of foreign patent numbers is available upon request to Morgan Advanced Materials plc.

Morgan Advanced Materials plc Registered in England & Wales at Quadrant, 55-57 High Street, Windsor, Berkshire SL4 1LP UK Company No. 286773